

Feb. 2022 Version

BestHard MA153

Premixed dry-shake floor hardener, super hard aggregate

Description:

BestHard MA153 is a high performance premixed floor hardener, ready to use. It consists of super hard synthetic aggregate, polymer, special chemicals and selected Portland cement .

Applications:

For special reinforcing of floor and slab surfacing in order to increase the resistance to abrasion and hence to reduce the formations of dust to severe mechanical wear such as: warehouses, quays, parking lots and mechanical engineering workshop, aircraft hangers, ...

Advantage:

- Premixed, easy apply, high and consistent quality.
- Improves resistance to abrasion.
- Improves resistance to impact.
- Improves resistance to oils and greases.
- Improves smoothness.
- Reduces dust formation.

Technical data:
Compressive strength:

≥ 70 N/mm² at 28 days. (ASTM C349-14)

Mohs hardness of aggregate:

≥ 9

Chemical resistance:

BestHard MA153 hardness as solid which improves better resistance to oils and greases after full curing time. However, BestHard MA153 have similar limitations of chemical resistance as other cement based cementitious products.

Supply form:

Dry powder.

Color:

Natural Grey, Green or as requested if PO reaches the minimum.

Bulk density:

1.6 kg/L.

Packaging:

25 kg/bag (bag with polyethylene liners).

Consumption:

~5.0 kg/m² (can be used more for specific purpose)

Waiting time for working:

Depending on the ambient temperatures and the type of cement and admixture used in the concrete, the waiting time for working of substrate can be vary a little. However, in the general condition, the waiting time should be as follow (for different using conditions):

- Pedestrian traffic: 2 ÷ 3 days.
- Light traffic: 7 ÷ 10 days.
- Normal traffic: 28 days.

BESTMIX CORPORATION
www.bestmix.vn

HEAD OFFICE:
Lot D1, D1&N3 Rd., Nam Tan Uyen IP,
Tan Uyen Town, Binh Duong Province,
Tel: (027) 4365 3990 - 4365 3991
Email: info@bestmix.com.vn

HCMC OFFICE 1:
378-384 Cong Hoa Str., Ward 13,
Tan Binh Dist., Ho Chi Minh City
Tel: (028) 3810 7995 (7996, 7997)
Email: bm1@bestmix.com.vn

HCMC OFFICE 2:
23 Nguyen Huu Canh Str., Ward 22,
Binh Thanh Dist., Ho Chi Minh City
Tel: (028) 3899 0339 - 3899 0340
Email: bm2@bestmix.com.vn

NHA TRANG OFFICE:
989 Le Hong Phong Street,
Phuoc Long Ward, Nha Trang City
Tel: 090 545 3579
Email: bm3@bestmix.com.vn

CENTRAL BRANCH:
478B1 Dien Bien Phu Street,
Thanh Khe District, Da Nang City
Tel: (023) 6371 5299 - 6371 5399
Email: bm4@bestmix.com.vn

NORTHERN BRANCH:
TT6.2 - 65, Dai Kim Urban Area,
Hoang Mai District, Ha Noi City
Tel: (024) 3200 8234
Email: bm5@bestmix.com.vn

| | |
|--------------------------|---|
| Storage: | As a basic rule it is recommended to store BestHard MA153 hardener in a dry and cool places. Do not stack more than 10 bags vertically. |
| Shelf life: | BestHard MA153 hardener powder has a shelf life of at least 12 months from the date of production with right storage conditions and unopened bag. |
| Application: | |
| Preparation: | Concrete mix design must be corresponding with using purpose. The vibrating and leveling work should be in right way to get optimum result. |
| Placing: | <p>BestHard MA153 should be applied in two layers by hand. Approximately 2/3 of quantity should be applied in the first layer and the balance in the second one. After the concrete has been evaporation of bleeding water, the preliminary floating is applied to leveling the surface and preventing cement slurry from concrete onto hardener in later time.</p> <p>Disperse the BestHard MA153 powder evenly by hand on the floor surface after preliminary floating. Should apply first on floor areas where the concrete is likely to loose moisture rapidly such as: near by walls, columns, joints and doorways... After the applied BestHard MA153 powder darkens in color indicating absorption of moisture from the concrete and when concrete has stiffened enough to prevent the float blades from digging into the surface, float the applied surface areas using power floats. Float just enough to bring the excess moisture to the surface.</p> <p>Apply second layer continuously as the first layer. Dispersing the remaining quantity of BestHard MA153 evenly on the first layer surface by hand, compensating with extra material over areas under-applied during the first dispersing. As soon as the second layer has darkened by moisture absorption, float the surface with a power trowel equipped with float blades or disc floats.</p> |
| Smooth finishing: | For the superior smooth finish, trowel again after further stiffening of the surface with slightly raised blades, but avoid raising them to angle that creates chatter marks or blisters on the surface. If either starts to appear, remove them by reducing the angle of trowel. |
| Curing: | Start curing immediately after final finishing using a liquid membrane-curing compound such as BestCure to prevent rapid evaporation of water to avoid surface split or spotted formation. |
| Safety: | BestHard MA153 is non toxic but alkaline like normal cement and can cause irritation with sensitive skin. Gloves, mask, goggles should always be worn |
| Disclaimer: | <i>The technical information and application instruction in documents of BESTMIX based on BESTMIX's current knowledge and practical experience. The information here only describes the general nature of product, so users should test the product for each purpose. BESTMIX has the right to change features of our product, user must always refer the latest technology product.</i> |