



BestClean RR112

Detergent of steel rust

Dec. 2018 Version

Description:	BestClean RR112 is the specialized detergent of steel rust in construction, it has the function of removing from moderate to heavy steel rust.
Application:	<ul style="list-style-type: none"> • Use to remove rust of steel due to long period of time, steel waiting at construction site. • Remove the rust from iron and steel contact with humidity, water, the rust of steel at buildings near sea. • Use to clean the surface of steel, metal and materials, tools made from steel (molds, steel formwork, ...)
Advantage:	<ul style="list-style-type: none"> • The ability to remove steel rust to level C (scale rust) according to TCVN 8790: 2011. • One component, easy to use, minimizes the risk during application. • Do not affect the adhesion strength between concrete or new materials on steel. • Does not cause corrosion of steel.

PRODUCT INFORMATION:

Appearance:	Light brown viscous liquid.
Package:	5 liters/ Can, 25 liters/ Can, 210 liters/ Drum
Storage condition:	Store in a dry and cool place.
Shelf life:	24 months in original.
Dosage:	One liter of product for 8 – 12 m ² iron and steel/ application layer (depending on the surface condition and the level of rust) For heavy rust of steel then need to apply at least 2 layers.

TECHNICAL DATA:

Density:	1.25 ± 0.02 kg/l (at 25°C)
pH:	< 3 (at 25°C)
Drying time of surface:	1 hour
Totally drying time:	3 hours
Ability to remove:	Level C according to TCVN 8790:2011

BESTMIX CORPORATION**HEAD OFFICE:**

Lot D1, D1&N3 Rd., Nam Tan Uyen IP,
Tan Uyen Town, Binh Duong Province.
Tel: (027) 4365 3990 - 4365 3991
Fax: (027) 4365 3992 Web:bestmix.vn

HCMC OFFICE 1:

378-384 Cong Hoa Str., Ward 13,
Tan Binh Dist., Ho Chi Minh City.
Tel: (028) 3810 7995 (7996, 7997)
Fax: (028) 3810 7998

HCMC OFFICE 2:

23 Nguyen Huu Canh Str., Ward 22,
Binh Thanh Dist., Ho Chi Minh City.
Tel: (028) 3899 0339 - 3899 0340
Fax: (028) 3899 0340

DANANG OFFICE:

478B1 Dien Bien Phu Street,
Thanh Khe District, Da Nang City.
Tel: (023) 6371 5299 - 6371 5399
Fax: (023) 6371 5499

HANOI OFFICE:

02 Biet Thu 5 Str., Linh Dam Pen.,
Hoang Liet, Thanh Xuan, Hanoi.
Tel: (024) 3200 8234 - 3200 8235
Fax: (024) 3200 8235

**INSTRUCTION:**

Surface cleaning: Preliminary cleaning of steel if the steel surface is dirty, grease and heavy layers easily peel off (if have)

Application: Use a brush, or sprayer to spray on the surface to be treated, or you can soak iron and steel directly into BestClean RR112 for 15-30 minutes. The following layer should be applied 5-20 minutes away from the previous layer.
After 3 hours from application, you can rinse the surface with clean water and pour concrete or use steel as usual.

NOTE:
Shake the product well before use.
Should be applied in dry conditions, and avoid contact with water. Do not dilute the product with water.
During the application process, if the steel surface is contacted with water, white particles will be attached to the steel, but that does not affect the steel's properties.

Cleaning, safety: The product may cause allergies to sensitive skin by prolonged contact. Should wear gloves, masks, and safety glasses when using the product. In case of getting into eyes, nose, mouth, ... should wash immediately with clean water several times before going to the nearest medical authority for timely and proper treatment.

Disclaimer:

The technical information and application instruction in documents of BESTMIX are based on BESTMIX's current knowledge and practical experience. The information here only describes the general nature of product, so users should test the product for each purpose. BESTMIX has the right to change features of our product, user must always refer the latest technology product.

BESTMIX CORPORATION**HEAD OFFICE:**

Lot D1, D1&N3 Rd., Nam Tan Uyen IP,
Tan Uyen Town, Binh Duong Province.
Tel: (027) 4365 3990 - 4365 3991
Fax: (027) 4365 3992 Web:bestmix.vn

HCMC OFFICE 1:

378-384 Cong Hoa Str., Ward 13,
Tan Binh Dist., Ho Chi Minh City.
Tel: (028) 3810 7995 (7996, 7997)
Fax: (028) 3810 7998

HCMC OFFICE 2:

23 Nguyen Huu Canh Str., Ward 22,
Binh Thanh Dist., Ho Chi Minh City.
Tel: (028) 3899 0339 - 3899 0340
Fax: (028) 3899 0340

DANANG OFFICE:

478B1 Dien Bien Phu Street,
Thanh Khe District, Da Nang City.
Tel: (023) 6371 5299 - 6371 5399
Fax: (023) 6371 5499

HANOI OFFICE:

02 Biet Thu 5 Str., Linh Dam Pen.,
Hoang Liet, Thanh Xuan, Hanoi.
Tel: (024) 3200 8234 - 3200 8235
Fax: (024) 3200 8235