

# BestRepair CE250

Surface-repairing mortar, Polymer-cement modified, one component

<b>Description</b>	BestRepair CE250 is surface repairing mortar, one component, polymer cement modified. It is a combination of: special cement, mineral and selected silicate mineral fibers, polymer, and special additives to make its chemical and physical properties.
<b>Uses:</b>	<p>BestRepair CE250 is used for all types of surfaces in medium and light loads such as:</p> <ul style="list-style-type: none"> <li>✓ Parking lot, pool bottom, water tank, prefabricated components ...</li> <li>✓ BestRepair CE250 is used for repairing finish surfaces: floor, wall, ceiling, ...which is honeycombed, damaged by erosion, impact, mechanical abrasion,...during use.</li> <li>✓ Recreating flatness for new surfaces that have not reached the flatness or gloss due to construction.</li> </ul>
<b>Advantage:</b>	<ul style="list-style-type: none"> <li>✓ One component is easy to use, minimizing risks during construction.</li> <li>✓ High plasticity, easy to adjust, so it saves labor and materials cost. Non-shrinkage, minimizing surface cracking.</li> <li>✓ Rapid and high-strength development, quickly put the project into use.</li> <li>✓ Improve abrasion resistance, chemical resistance, and waterproof ability.</li> <li>✓ Non-toxic, can be used for water reservoirs. Non-chloride, non-corrosive.</li> <li>✓ Suitable for Vietnamese climate conditions.</li> </ul>

## SPECIFICATION

<b>Existence form:</b>	Dry fine powder.
<b>Color:</b>	Grey cement.
<b>Density:</b>	Dry powder form: $2.65 \pm 0.02$ kg/liter.    Wet form: $2.23 \pm 0.02$ kg/liter.
<b>Storage condition:</b>	Unopened bag, cool and dry place.
<b>Shelf life:</b>	At least 12 months in storage condition.
<b>Packing:</b>	25 kg/bag.
<b>Consumption:</b>	74÷75 bags for 1m <sup>3</sup> mortar.

# TECHNICAL DATA:

Mixing water (%)	Size of particle (mm)	Shrinkage (%)	Layer thickness (mm)	Pot life (minute)
15÷17	< 0.5	< 1	1÷5	< 30

## Minimum strength:

Old days	01 day	03 days	07 days	28 days
Compressive strength <sup>(*)</sup> (MPa)	≥ 10	≥ 15	≥ 20	≥ 25
Flexural strength <sup>(*)</sup> (MPa)	≥ 1.0	≥ 1.5	≥ 2.0	≥ 2.5
Bonding strength <sup>(**)</sup> (MPa)	NA	NA	NA	≥ 1.5

(\*): Standard: ASTM C348; ASTM C349.

(\*\*): Standard: ASTM D7234-05

## INSTALLATION

### Surface preparation:

The surface to be repaired must be properly treated, and all loose materials and impurities must be removed.  
Avoid spreading grease, or oil,...using high-pressure water to clean the surface before constructing.  
If the surface is dry, moisten it with clean water.

### Mixing:

Pouring BestRepair CE250 slowly into properly freshwater (water ratio from 15-17% compared to the weight of powder as about 3.75-4.25 liter of fresh water for 25 kg) continuously stirring with electric mixer at speed 300 ÷ 400 revolutions/ minute about 05 minutes until the mixture is free of lumps and homogeneous is as required.

### Application:

Use a brush to apply the bonding layer of BestLatex R114 (see the application document of BestLatex R114) over the entire surface prepared as above.  
Apply the mortar layer of BestRepair CE250 was thoroughly mixed with water on the surface while the layer of BestLatex R114 is still wet. Ensure the BestRepair CE250 mortar is compacted to the surface.  
The maximum thickness of the mixture is not greater than 20 mm. In case of the thickness of the substrate which is needed repair is greater than 20mm, apply once more layer when the previous is hardened.

### Curing:

Curing regular requirement as others cement base products. Reduce free of water by covering wet cloth, plastic cover, or cure compound BestCure AC015 or BestCure SS015.

### Safety:

BestRepair CE250 is alkalinity, should wear gloves, masks, and glasses while handling the product. In case of accidental eye contact, wash with fresh water and seek medical advice immediately.

### Disclaimer:

*The technical information and application instructions in documents of BESTMIX are based on BESTMIX's current knowledge and practical experience. The information here only describes the general nature of the product, so users should test the product for each purpose. BESTMIX has the right to change the features of our product, user must always refer to the latest technology product.*

## BESTMIX CORPORATION

www.bestmix.vn

**HEAD OFFICE:**  
Lot D1, D1&N3 Rd., Nam Tân Uyên IP,  
Tân Uyên Town, Bình Dương Province  
Tel: (027) 4365 3990 - 4365 3991  
Email: info@bestmix.com.vn

**HCMC OFFICE 1:**  
378-384 Cong Hoa Str., Ward 13,  
Tân Bình Dist., Ho Chi Minh City  
Tel: (028) 3810 7995 (7996, 7997)  
Email: bm1@bestmix.com.vn

**HCMC OFFICE 2:**  
23 Nguyen Huu Canh Str., Ward 22,  
Binh Thanh Dist., Ho Chi Minh City  
Tel: (028) 3899 0339 - 3899 0340  
Email: bm2@bestmix.com.vn

**NHA TRANG OFFICE:**  
989 Le Hong Phong Street,  
Phuoc Long Ward, Nha Trang City  
Tel: 090 545 3579  
Email: bm3@bestmix.com.vn

**CENTRAL BRANCH:**  
47881 Dien Bien Phu Street,  
Thanh Khe District, Da Nang City  
Tel: (023) 6371 5299 - 6371 5399  
Email: bm4@bestmix.com.vn

**NORTHERN BRANCH:**  
TT6.2 - 65, Dai Kim Urban Area,  
Hoang Mai District, Ha Noi City  
Tel: (024) 3200 8234  
Email: bm5@bestmix.com.vn