



July 2018 Version

BestTile CE150

Tile adhesive, Improved the cement-polymer original, one component.

Description: BestTile CE150 is tile adhesive, improved the cement-polymer original, ready mixed, one component. Just mix with water to use. BestTile CE150 is made of special cement, selected siliceous aggregate and special additives, and polymer modified.

Recommended for:

- Paste tile, floor, terrace,...
- Paste the tile wall type vertical wall, tilt wall,...
- Paste the decorative tile, antique brick and concrete,...
- Paste the roofing tile, and decorative tile in special cases.
- Paste the mineral fiber plate panels used for sound insulation, and heat,...

Advantage:

- High plasticity, high adhesion, application and modification time is long, easy to apply, saving material and labor.
- The higher waterproof than traditional mortar because the component contains special additives.
- Ready mixed, one component, regularly quantitative of components should be easy to use, avoid risks in the process of preparation on site.
- The strength develops fast and highly, put into use early.
- Improve the aesthetic value of the project.
- Non-toxic, can be used for domestic water tanks.
- Does not contain chloride corrosion of reinforcement.
- Suitable climatic conditions in Vietnam.

Technical data:

Existence form:	Dry powder.
Color:	Grey, other colors upon request.
Compressive strength:	≥ 15 MPa.
Bonding strength:	≥ 1.0 MPa.
Density:	Dry powder: 2.60 ± 0.02 kg/liter. Wet : 1.80 ± 0.02 kg/liter .
Water ratio:	20 ÷ 22 % compared with powder weight.
Consumption:	Average: 1.65 kg dry powder/1m ² /1mm.
Holding conditions:	Unopened bag, moisture resistance, take a dry and cool place.
Shelf life:	At least 12 months from the date of manufacture.
Package:	25 kg/bag.

PHỤ GIA & HÓA CHẤT XÂY DỰNG BESTMIX® CONSTRUCTION CHEMICALS & ADMIXTURES

BESTMIX CORPORATION
www.bestmix.vn

HEAD OFFICE:
Lot D1, D1&N3 Rd., Nam Tan Uyen IP,
Tan Uyen Town, Binh Duong Province.
Tel: (027) 4365 3990 - 4365 3991
Email: info@bestmix.com.vn

HCMC OFFICE 1:
378-384 Cong Hoa Str., Ward 13,
Tan Binh Dist., Ho Chi Minh City
Tel: (028) 3810 7995 (7996, 7997)
Email: bm1@bestmix.com.vn

HCMC OFFICE 2:
23 Nguyen Huu Canh Str., Ward 22,
Binh Thanh Dist., Ho Chi Minh City
Tel: (028) 3899 0339 - 3899 0340
Email: bm2@bestmix.com.vn

NHA TRANG OFFICE:
989 Le Hong Phong Street,
Phuoc Long Ward, Nha Trang City
Tel: 090 545 3579
Email: bm3@bestmix.com.vn

CENTRAL BRANCH:
478B1 Dien Bien Phu Street,
Thanh Khe District, Da Nang City
Tel: (023) 6371 5299 - 6371 5399
Email: bm4@bestmix.com.vn

NORTHERN BRANCH:
TT6.2 - 65, Dai Kim Urban Area,
Hoang Mai District, Ha Noi City
Tel: (024) 3200 8234
Email: bm5@bestmix.com.vn

Substrate preparation:	The surface should be cleaned as required, dirt, moss, and mold,...to be completely removed by appropriate means. In particular, if the surface is contaminated with oil, or grease,... be thoroughly treated before applying BestTile CE150. Should wet the surface before applying for at least 05 minutes.
Mixing:	Use a clean basket with appropriate capacity, pour the mixing water before, the stirring speed 300 ÷ 400 circles/mins, run and continue to pour slowly BestTile CE150 mixing until homogenous. Mixing time is normally about 05 minutes. However, depending on the specific conditions to determine the appropriate mixing time to ensure homogenous mixtures, without lumps.
Application:	Use an iron brush or plastic with an appropriate sawtooth to apply compound BestTile CE150 on the surface. The tile work is carried bottom-up and horizontal application. Use a rubber hammer and other tools to edit the appropriate location of bricks as desired. The time allowed for application and editing can be extended to 30 minutes from mixing BestTile CE150 with water. However, this depends on the environmental condition of temperature, wet surface condition,... Note: The application time and editing are not over 60 minutes from mixing. Do not add any other materials into BestTile CE150 when using (except mixing water). Do not use material is overtime for application.
Cleaning:	Clean tools and equipment after application and before material sets.
Safety:	BestTile CE150 is non-toxic. However, could make an allergy to sensitive skin. Do not contact it a long time. Should wear labor protection when application. Avoid contacting directly food, instruments of live activity, and keep out of the reach of children. In case of accidental eye contact, wash with fresh water and seek medical advice immediately.

Disclaimer: *The technical information and application instruction in documents of BESTMIX based on BESTMIX's current knowledge and practical experience. The information here only describes the general nature of product, so users should test the product for each purpose. BESTMIX has the right to change features of our product, user must always refer the latest technology product.*

BESTMIX CORPORATION
www.bestmix.vn

HEAD OFFICE: Lot D1, D1&N3 Rd., Nam Tan Uyen IP, Tan Uyen Town, Binh Duong Province. Tel: (027) 4365 3990 - 4365 3991 Email: info@bestmix.com.vn	HCMC OFFICE 1: 378-384 Cong Hoa Str., Ward 13, Tan Binh Dist., Ho Chi Minh City Tel: (028) 3810 7995 (7996, 7997) Email: bm1@bestmix.com.vn	HCMC OFFICE 2: 23 Nguyen Huu Canh Str., Ward 22, Binh Thanh Dist., Ho Chi Minh City Tel: (028) 3899 0339 - 3899 0340 Email: bm2@bestmix.com.vn	NHA TRANG OFFICE: 989 Le Hong Phong Street, Phuoc Long Ward, Nha Trang City Tel: 090 545 3579 Email: bm3@bestmix.com.vn	CENTRAL BRANCH: 478B1 Dien Bien Phu Street, Thanh Khe District, Da Nang City Tel: (023) 6371 5299 - 6371 5399 Email: bm4@bestmix.com.vn	NORTHERN BRANCH: TT6.2 - 65, Dai Kim Urban Area, Hoang Mai District, Ha Noi City Tel: (024) 3200 8234 Email: bm5@bestmix.com.vn
--	---	--	---	---	---